Lifting Solutions Group
Axel Johnson International

Web Sling Connector X-016

Product information



At least 25% greater WLL than traditional Grade 8 products.
Proof Load tested at 2.5 times the WLL with certification for each batch manufactured.
Fatigue rated to 20,000 cycles at 1.5 times the WLL.
Tempering temperature minimum 400°C

... *Read more*

Material: Quenched and Tempered Alloy Steel.
Marking: According to standard, Type, manufacturer ID, traceability.
Temperature range: -40° up to +200°C (without reduction in WLL).
Finish: Blue painted.
Standard: EN 1677-1

Safety factor: 4:1
Grade: 10


Certex Latvija
info@certex.lv
+371 67611882

© November 2026 - All Rights Reserved

Lifting Solutions Group
Axel Johnson International

Web Sling Connector X-016

Blueprint



Technical data

Part code	Chain diameter mm	WLL ton	A mm	B mm	D mm	K mm	W mm	Weight kg
402200140200	6	1.4	15	17	7	56	39	0.2
402200250200	7-8	2.5	18	23	9	63	39	0.3
402200400200	10	4	25	27	11	77	46	0.6
402200670200	13	6.7	30	37	16	97	53	1.1
402201000200	16	10	36	39	19	114	66	2
402201600200	20	16	42	46	22	132	79	3.2
402201900200	22	19	49	59	24	188	124	7.7

Certex Latvija
info@certex.lv
+371 67611882

© November 2026 - All Rights Reserved