
Lifting Solutions Group
Axel Johnson International

Steel Wire Rope 1x7

Product information

S Z A



... Read more

Rope construction: 1x7
Marking: According to standard
Standard: SS 424 08 06

Fill factor: 0.78

Stay rope



Certex Latvija
info@certex.lv
+371 67611882

© November 2026 - All Rights Reserved

Lifting Solutions Group
Axel Johnson International

Steel Wire Rope 1x7

Technical data

Part code	Rope diameter mm	Tensile strength N/mm²	Finish	Rope lay	Min. breaking force kN	Steel area mm²	Lubrication	Weight kg/100m
100100641520020	6.4	1,370/1,420	Heavy galvanized	S	32	25	Dry	19
100100642520020	6.4	1,370/1,420	Heavy galvanized	Z	32	25	Dry	19
100100731520020	7.3	1,370/1,420	Heavy galvanized	S	43	33	Dry	26
100100732520020	7.3	1,370/1,420	Heavy galvanized	Z	43	33	Dry	26
100100921520020	9.2	1,370/1,420	Heavy galvanized	S	68	52	Dry	41
100100922520020	9.2	1,370/1,420	Heavy galvanized	Z	68	52	Dry	41
100101061520020	10.6	1,370/1,420	Heavy galvanized	S	89	68	Dry	54
100101062520020	10.6	1,370/1,420	Heavy galvanized	Z	89	68	Dry	54
100101211520020	12.1	1,370/1,420	Heavy galvanized	S	116	89	Dry	70
100101212520020	12.1	1,370/1,420	Heavy galvanized	Z	116	89	Dry	70

Certex Latvija
info@certex.lv
+371 67611882

© November 2026 - All Rights Reserved